

## **solvoprint paper 240 satin**

### Technical Information

#### ➤ **General Information**

- ca. 240 g/m<sup>2</sup> heavy paper with satin shiny surface
- high-grade paper, high weight
- very good printability and handling
- good water – and scratch resistance after complete drying
- bright white print side

#### ➤ **Areas of Application**

- printable with eco solvent and solvent inks as well as with UV-curable inks
- high definition and print quality
- ideally suitable for photo prints, posters, graphics, etc.
- suitable for indoor applications

#### ➤ **Processing & Handling**

- for further handling and storage recommendations please refer to the latest product catalogue or visit our homepage under [www.neschen.de](http://www.neschen.de)
- to avoid fingerprints, usage of cotton gloves is recommended
- to prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured)
- must not be stored lying flat, storage is best to be done in the original box
- when hot laminating make sure that the heat comes from upper **and** lower roller

#### ➤ **Advantages / Special Features**

- bright colours with high brilliance and photorealistic print quality
- all-purpose media; very versatile
- top-quality impression by high weight
- for more information please also see the latest Neschen compatibility list “solvoprint media”

## solvoprint paper 240 satin

### Technical Information

#### ➤ Technical Data

##### ➤ Carrier

<b>carrier material:</b>	paper with solvent Inkjet coating	
<b>thickness [<math>\mu\text{m}</math>]:</b>	232 $\pm$ 6	
<b>weight [<math>\text{g}/\text{m}^2</math>]:</b>	219 $\pm$ 5	
<b>gloss level [scales]:</b>	ca. 50	Dr. Lange Reflektometer , 60°
<b>whiteness [CIE Ganz 82]:</b>	L: 96,5 a: 0,3 b: 0,8	

##### ➤ Others

<b>storage conditions:</b>	original boxed at 5 – 40°C / 40 - 104° F / at R.H. 30 - 90% keep dry / indoor
<b>material durability [years]:</b>	1
<b>temperature resistance:</b>	

All tests were performed in accordance with 23/50-2, DIN 50014.