

ASLAN WB 995

The opaque whiteboard film

This self-adhesive whiteboard film is ideal for often changing scripts, for example in seminar- and meeting rooms, schools and kindergartens. But also at hotel receptions or in medical offices they make every even surface to an information board.

The high quality whiteboard film characterises through its long durability and the easy handling. Resistant to dirt and splashing water it is easy to clean. Writings can be wiped dry without leaving ghostwritings.

ASLAN recommends the use of whiteboard-markers.

For any further information please contact our technical advisory service:
+49 (0)2204.708-80

CONSTRUCTION

face-film:	PET/PVC - compound	
thickness:	~ 150 µm	
adhesive:	acrylic pressure adhesive	square quantity: ~ 22 g/m ²
release liner:	silicone cardboard	square weight: ~ 140 g/m ²

CHARACTERISTICS

adhesive strength: (ASTMD-903)	immediately after 1 week	~ 2.5 N/25 mm ~ 12.5 N/25 mm
dimensional stability:	applicated onto aluminium after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.45 %
chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalis and salts.	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C

ASLAN WB 995

PROCESSING

- application:** Dry application only, because due to the compound longer drying periods can occur.
For the application of letterings etc. we recommend our ASLAN application tapes respectively the ASLAN TMO.
- storage life:** Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

state: 11|2008

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

POB 5165 · D-51486 Overath · Oberauel 2 · D-51491 Overath · Germany
fon +49(0)2204.708-80 · **fax** +49(0)2204.708-50 · **e-mail** info@ASLAN-schwarz.com

www.ASLAN-schwarz.com