

PolySOL Roll-up Film 180

■ satin 3515 - 180 µm

Satin finished, waterfast polyester film for solvent inks. Due to the greyback, opacity reaches more than 99.9%. It is suitable for free-standing roll-up applications. The excellent flatness allows this media to be used for a wide range of signage, advertising and POS applications. The innovative coating and the bright white lead to quick drying and a wide colour gamut with eco-, mild- and true-solvent inks. The product is suitable for both hot and cold lamination.

Applications

- Indoor signs
- Indoor adverts
- Pop-up Displays
- Outdoor signage

Advantages

- Greyback offers high opacity
- Quick dry
- Tear resistant polyester base
- Waterfast prints
- High colour brilliance

PolySOL Roll-up Film 180

■ **satin 3515 - 180 µm**

List of Printers

Printer	Ink	Quality
Hewlett Packard DJ 8000S / 9000S / 10000S	Inkjet mit Eco Solvent	Excellent
Hewlett Packard DJ L65500 Latex ink	Inkjet mit IR- / Latex Tinte	Good
Hewlett Packard DJ L25500 / 26500 / 28500 - Latex 260 / 280	Inkjet mit IR- / Latex Tinte	Excellent
Hewlett Packard Scitex LX 600	Inkjet mit IR- / Latex Tinte	Good
Hewlett Packard Scitex LX 800 / LX 820 / LX 850	Inkjet mit IR- / Latex Tinte	Good
Epson Stylus Pro GS6000 UltraChrome GS	Inkjet mit Eco Solvent	Excellent
Epson SureColor SC-30600 / 50600 / 70600	Inkjet mit Eco Solvent	Good
Roland SolJet SJ540 / SC540 SJ 740 / SC740	Inkjet mit Eco Solvent	Excellent
Roland VersaCAMM SP-300i / SP-540i	Inkjet mit Eco Solvent	Good
Roland VersaCAMM VP-300i / VP-540i	Inkjet mit Eco Solvent	Excellent
Roland VS 540 / VS 640	Inkjet mit Eco Solvent	Excellent
Roland SolJET PRO4 XR-640	Inkjet mit Lösemitteltinte	Excellent
Mimaki JV-3 160S, 250	Inkjet mit Lösemitteltinte	Good
Mimaki JV 5-130 / -160 / -260 / -320	Inkjet mit Eco Solvent	Good
Mimaki CJV 30	Inkjet mit Eco Solvent	Excellent
Mimaki JV 33 / JV34 - 260	Inkjet mit Eco Solvent	Good
Mimaki JV 400	Inkjet mit IR- / Latex Tinte	Good
Mutoh Toucan	Inkjet mit Lösemitteltinte	Good
Mutoh Rockhopper II 50", 64", 87"	Inkjet mit Eco Solvent	Good
Mutoh ValueJet 1204 / 1304 / 1614	Inkjet mit Eco Solvent	Good
Mutoh Valuejet 1204 / 1304 / 1324 / 1614 / 1624 / 1638	Inkjet mit Eco Solvent	Good
Océ CS6060	Inkjet mit Eco Solvent	Good
Océ CS9360 / CS935	Inkjet mit Eco Solvent	Excellent

Last update: 30.10.2012

PolySOL Roll-up Film 180**■ satin 3515 - 180 µm****Physical Properties**

Test conditions	23°C / 50% R.F:	
Weight (Total) [gsm]	235	ISO 536
Thickness (total) [microns]	185	ISO 534
Opacity [%]	>99	ISO 2471
Gloss (60°) [%]	16	ISO 2813

Recommended use and storage

To maintain quality the paper should be stored and converted under the following conditions of 30-65% relative humidity and at temperatures of 10-30 °C. Lamination (hot/cold) is recommended to secure long lasting unchanged image quality. Over time unprotected dye colours will deteriorate through atmospheric processes (does not apply to pigment colours).

The values provided on this datasheet are only for orientation.

Before using our media please check its compatibility for your printer and intended application. Technical specifications are subject to change, therefore we do not take responsibility for any misprints resulting from technically modified inks and/ or printers. 04.06.2012